

Concrete repair and restoration punch checklist

Concrete repair and restoration punch is where small misses become callbacks after the crew has demobilized. This checklist walks the finished work the way the owner and the next trade will see it, with the photo that closes each item instead of a note that reopens it. Work is commonly verified against ICRI guidance, ACI, manufacturer's published instructions. Confirm the edition your authority having jurisdiction has adopted.

Who runs it: The restoration foreman on a callback, with the GC's superintendent closing repair punch items. When: During closeout, after the repairs have cured fully and any coating or sealer reveals blending and bond issues.

Trace and repair

- ☐ Each defect located and photographed in context
A close shot of the crack, drummy area or off-color patch plus a wide shot placing it on the elevation or slab **2 photos required**
- ☐ Drummy or cracked patches re-sounded and re-worked
Debonded areas removed and re-placed rather than surface-filled, re-sounded solid after re-work, edge cracks traced to their cause. **2 photos required**

Blend and closure

- ☐ Color and finish blended on the cured repair
Blending judged against the surrounding surface once dry, not while wet, so the repair reads consistent after cure. **1 photo required**
- ☐ No remaining repair items before signoff
All repair punch items closed with photos before the area is released for coating, sealing or turnover. **1 photo required**