

Concrete slab moisture mitigation punch checklist

Concrete slab moisture mitigation punch is where small misses become callbacks after the crew has demobilized. This checklist walks the finished work the way the owner and the next trade will see it, with the photo that closes each item instead of a note that reopens it. Work is commonly verified against manufacturer's published instructions, ASTM F3010 / F710 guidance. Confirm the edition your authority having jurisdiction has adopted.

Who runs it: The applicator on a callback, or the GC's superintendent closing mitigation items before flooring. When: During closeout on the coated slab, after other trades have walked and staged on it and before flooring covers the membrane for good.

Defect repair

- ☐ **Pinholes and holidays found and recoated**
Slab rechecked under raking light, each pinhole or skip marked and recoated to tie into the surrounding film, not just spotted over. 2 photos required
- ☐ **Delaminated areas cut back and re-prepped**
Loose or blistered coat removed to sound, bonded material, the area re-prepped and recoated rather than layered over the failure. 1 photo required

Edges and signoff

- ☐ **Edge and penetration touch-up completed**
Perimeter and penetration tie-ins touched up where staging or traffic nicked them, continuity restored at every termination. 2 photos required
- ☐ **No remaining mitigation items before flooring release**
All punch items closed with photos and the coat confirmed continuous before flooring is released over the area. 1 photo required